

### 3- SPECIFICATION SYTEM FOR FLOOR COATING :

PRETREATMENT:	STEEL ,BLAST AND CLEANED TO ISO SA2.5-SA3 CEMENT AND CONCRETE MUST BE CLEAN FROM GREASE,OIL AND OTHER CONTAMINATION	
PAINT SYSTEM:		
FARCO SEAL 13	1 × 60μ	SEALER EPOXY SOLVENT FREE
FARCO FLOOR 131	<u>1 × 3000μ</u>	FLOOR COATING
TOTAL D.F.T:	<u>3060μ</u>	