

ZINC RICH EPOXY PRIMER

Product information

- 1-Good anticorrosive properties.
- 2-Good adhesion on cold rolled steel.
- 3-Easily applied by airless or conventional spray.
- 4-Can be used with a wide range of topcoats.
- 5-Tough and adherent primer providing excellent resistance to corrosion.
- 6-Outstanding resistance to water, weather.
- 7-Superior performance on marine, hulls, decks and superstructure.
- 8-Combine epoxy's toughness with zinc's superior protection.

Physical data

Colour:	grey
Finish:	Flat
Flash point:	
resin:	34°C
cure:	36°C
solvent:	28 °C
Volume solids:	60 ±2%
D.F.T:	50-70 microns
Specific gravity(mixed):	2.55 ± 0.05gr/cm ³
Theoretical coverage:	12 m ² /lit (at 50 µ D.F.T)
Drying time at 25°C:	
touch dry:	3 hrs
dry to handle :	6-8 hrs
full cure:	7 days
Component:	2
Pot life:	8 hrs at 25 °C
Mixing ratio(by volume):	
resin(a):	refer to can label
cure(b):	refer to can label
Application methods:	conventional spray or brush or airless spray or roller
Recoat intervals* :	10°C 25°C 40°C
(mild condition) : Min:	25 hrs 12 hrs 5 hrs
Max:	70 hrs 36 hrs 18 hrs
Recommended thinner:	FARCO THINN 10
Recommended cleaner:	FARCO CLEAN 10
Shelf life:	6 months when stored indoors in unopened original containers at 5 to 40°C (cool and dry place).
Curing mechanism:	by solvent release and reaction by curing agent and resin
Substrate:	steel

*: For recoating the surface should be free of dust ,grease and contamination .

Head Office: 3rd Flr, Building #4. Bahar 4 Alley, W. Gamsar Str. S. Sheikh Bahaei Str. Tehran- Iran.

Tel: +98 (21) 88613776

Fax: +98 (21) 88613775

Web site: www.ranganfar.com

Email: info@ranganfar.com

**R
A
N
G
A
N

F
A
R**

Typical uses

Rangan Far zinc rich epoxy primer is a fast drying polyamide cured that used on abrasive blast, cleaned Steel.

Other uses are:

Decks, hulls, barges and workboats, machinery, pipes and tank exteriors, oil refineries, Power plants, chemical process and waste treatment plants.

Application information

This Rangan Far's product is two component polyamide cured zinc rich epoxy primer.

To obtain the maximum performance for which rangan far's is formulated, strict adherence to all application instructions, precautions, conditions and limitations is necessary.

Application equipment

The following equipment is listed as a guide and suitable equipment from other manufactures may be used:

1-Airless spray: standard airless spray equipment having a 28:1 or higher pump ratio and a fluid tip with a 0.330 to 0.660 mm Orifice.

2-Conventional spray: industrial equipment with pressure feed tank with suitable aircap having a fluid tip with a 2 – 2.2 mm orifice .

3 -Mixer: mixer must be powered by an air motor or an explosion proof electric motor.

4-Brush or roller.

Caution

1-Handle with care.

2-Avoid inhalation of possible solvent vapours or paint mist, as well as paint contact with skin and eyes.

3-Apply only in well ventilated areas and ensure that adequate forced ventilation exists when paint applies is in confined spaces or when the air is stagnant.

4-Always take precautions against the risks of fire and explosions.

5-Harmful or fatal if swallowed, immediately seek medical assistance.

6-Use fresh air masks and explosion proof equipment.

R
A
N
G
A
N

F
A
R

Application procedures

- 1-Flush equipment with cleaner before use.
- 2-Stir resin to an even consistency with a power mixer.
- 3-Add cure to resin and continue stirring for 5 minutes.
Note: since the pot life is limited and shortened by high temperatures ,do not mix more material than will be used in 8 hours at 25 °C.
- 4- Thinning with FARCO THINN 10 for necessary
- 5-Stir during application to maintain uniformity of material and apply a wet coat in even parallel passes after 20 minutes.
- 6-Clean all equipment with cleaner immediately after use.

Environmental condition

Environmental temperature must be 10-40°C.
Surface temperature must be at least 3°C above dew point to prevent condensation. At freezing temperature surface must be free of ice and relative humidity below 80 %.

Surface preparation

Sand blasting to a standard
Sa 2.5 – Sa3 , SIS 05 5900 , ISO 8501-1.

**R
A
N
G
A
N

F
A
R**

This document was created with Win2PDF available at <http://www.daneprairie.com>.
The unregistered version of Win2PDF is for evaluation or non-commercial use only.