

ETHYL SILICATE TOP COAT

Product information

- 1-Outstanding resistance against weathering and abrasion.
- 2-Excellent chemical resistance with in PH range 5.5-9.5.
- 4-Low voc.
- 5-Resist temperatures up to 400°C.

Physical data

Colour:	white		
Finish:	flat		
Flash point:			
resin:	11°C		
cure:	-		
solvent:	-		
Volume solids:	59 ±4%		
D.F.T:	50-75 microns		
Specific gravity(mixed):	1.87 ±0.1 gr/cm ³		
Theoretical coverage:	11.8 m ² /lit (at 50μ d.f.t)		
Drying time at 20°C:			
touch dry:	5 -10 min (at relative humidity 56%)		
dry to handle :	2 hrs (at relative humidity 56%)		
full cure:	5 days (at relative humidity 56%)		
Component:	2		
Pot life:	min 3 hrs at 25°C		
Mixing ratio(by volume):			
resin:	refer to can label		
powder:	refer to can label		
Application methods:	brush ,conventional spray or airless spray		
Recoat intervals*:	10°C	25°C	40°C
(mild condition) : Min:	4 hrs	2 hrs	1 hrs
Max:	50 hrs	24 hrs	12 hrs
Recommended thinner:	FARCO THINN 50		
Recommended cleaner:	FARCO CLEAN 50		
Shelf life:	6 months when stored indoors in unopened Original containers at 5 to 40°C (cool and dry Place).		
Curing mechanism:	by solvent release and reaction with atmospheric moisture		
Substrate:	primed steel ,		

*: For recoating the surface should be free of dust ,grease and contamination .

R
A
N
G
A
N

F
A
R

Head Office: 3rd Flr, Building #4. Bahar 4 Alley, W. Gamsar Str. S. Sheikh Bahaei Str. Tehran- Iran.

Tel: +98 (21) 88613776

Fax: +98 (21) 88613775

Web site: www.ranganfar.com

Email: info@ranganfar.com

Typical uses

As a top coat in paint systems for long-life protection of steel exposed to moderately to severely corrosive environment.

Application information

This rangan far's product is inorganic silicate coating for industrial and chemical use.

To obtain the maximum performance for which this product is formulated, strict adherence to all application, instructions, precautions, conditions and limitations is necessary.

Application equipment

The following equipment is listed as a guide and suitable equipment from other manufactures may be used.

Adjustments of pressure and change of tip size may be needed to obtain the proper spray characteristics.

1-Airless spray: standard airless spray equipment, having a fine finish tip with a 0.4 mm to a 0.55 mm or larger.

2-Conventional spray: industrial equipment with suitable aircap having a fluid tip with a 1.4-1.6 mm orifice .

3-Mixer: mixer must be powered by an air motor or an explosion proof electric motor.

Caution

1-Handle with care.

2-Avoid inhalation of possible solvent vapours or paint mist, as well as paint contact with skin and eyes.

3-Apply only in well ventilated areas and ensure that adequate forced ventilation exists when applying paint in confined spaces or when the air is stagnant.

4-Always take precautions against the risks of fire And explosions.

5-Harmful or fatal if swallowed, immediately seek medical assistance.

6-Use fresh air masks and explosion proof equipment.

**R
A
N
G
A
N

F
A
R**

Application procedures

- 1-Flush equipment with recommended cleaner before use.
- 2-Stir resin to an even consistency with a power mixer.
- 3-Add powder to resin little by little and continue stirring for

5 minutes .

Note: since the pot life is limited and shortened by high Temperatures ,do not mix more material than will be used In 3 hours at 20 °C.

- 4-Stir during application to maintain uniformity of material and apply a wet coat in even parallel passes.

- 5-Clean all equipment with cleaner immediately after use.

Environmental condition

Environmental temperature must be 10-40°C.

Surface temperature must be at least 3°C above dew point to prevent condensation. At freezing temperature surface must be free of ice and relative humidity below 80 %.

Surface preparation

The surface must be clean and dry .all dirt grease and other foreign materials should be removed .old primed surface must be smoothly wire brushed.

**R
A
N
G
A
N

F
A
R**

This document was created with Win2PDF available at <http://www.daneprairie.com>.
The unregistered version of Win2PDF is for evaluation or non-commercial use only.